


Hydro-Clearcoat

WO1868GR999A / RRS W CLEARCOAT HG

Characteristics	<ul style="list-style-type: none"> ■ Water-thinnable baking coating ■ Application, e.g. in the automotive sector ■ Good mechanical resistance ■ Good light and weather resistance ■ Good chemical resistance ■ Good scratch resistance 																				
Technical / Physical Data	<table border="1"> <tr> <td>■ Binder-Base</td> <td>Combination of acrylate/amino resin</td> </tr> <tr> <td>■ Colour</td> <td>colourless</td> </tr> <tr> <td>■ Gloss value visual</td> <td>high glossy</td> </tr> <tr> <td>■ Viscosity DIN 53211 (formerly)</td> <td>Flow time 16-18 seconds 4 mm viscosity cup</td> </tr> <tr> <td>■ Thinner</td> <td>demineralised water</td> </tr> <tr> <td>■ pH-Value</td> <td>8,2-8,5</td> </tr> <tr> <td>■ Density calculated</td> <td>1,00-1,02 g/ml</td> </tr> <tr> <td>■ Solid Mass calculated</td> <td>24-26 %</td> </tr> <tr> <td>■ Solid content in volume calculated</td> <td>200-220 ml/kg</td> </tr> <tr> <td>■ Material usage theoretical, without application loss</td> <td>135-150 g/m², Layer thickness 30 µm</td> </tr> </table>	■ Binder-Base	Combination of acrylate/amino resin	■ Colour	colourless	■ Gloss value visual	high glossy	■ Viscosity DIN 53211 (formerly)	Flow time 16-18 seconds 4 mm viscosity cup	■ Thinner	demineralised water	■ pH-Value	8,2-8,5	■ Density calculated	1,00-1,02 g/ml	■ Solid Mass calculated	24-26 %	■ Solid content in volume calculated	200-220 ml/kg	■ Material usage theoretical, without application loss	135-150 g/m ² , Layer thickness 30 µm
■ Binder-Base	Combination of acrylate/amino resin																				
■ Colour	colourless																				
■ Gloss value visual	high glossy																				
■ Viscosity DIN 53211 (formerly)	Flow time 16-18 seconds 4 mm viscosity cup																				
■ Thinner	demineralised water																				
■ pH-Value	8,2-8,5																				
■ Density calculated	1,00-1,02 g/ml																				
■ Solid Mass calculated	24-26 %																				
■ Solid content in volume calculated	200-220 ml/kg																				
■ Material usage theoretical, without application loss	135-150 g/m ² , Layer thickness 30 µm																				
Substrate	<ul style="list-style-type: none"> ■ Light alloy wheels 																				
Pretreatment	<ul style="list-style-type: none"> ■ The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate. Chromating or corresponding chrome-free conversion coatings. 																				
Structure recommendation	<table border="1"> <tr> <td>■ Substrate</td> <td>on light alloy wheels</td> </tr> <tr> <td>■ Primer</td> <td>RRS PRIMER Dry film thickness 120 µm</td> </tr> <tr> <td>■ Base coat</td> <td>RRS W / S Dry film thickness 20 µm</td> </tr> <tr> <td>■ Top coat</td> <td>RRS CLEARCOAT AC / PE Dry film thickness 80 µm</td> </tr> <tr> <td>■ Clear coat</td> <td>RRS W CLEARCOAT HG Dry film thickness 30 µm</td> </tr> </table>	■ Substrate	on light alloy wheels	■ Primer	RRS PRIMER Dry film thickness 120 µm	■ Base coat	RRS W / S Dry film thickness 20 µm	■ Top coat	RRS CLEARCOAT AC / PE Dry film thickness 80 µm	■ Clear coat	RRS W CLEARCOAT HG Dry film thickness 30 µm										
■ Substrate	on light alloy wheels																				
■ Primer	RRS PRIMER Dry film thickness 120 µm																				
■ Base coat	RRS W / S Dry film thickness 20 µm																				
■ Top coat	RRS CLEARCOAT AC / PE Dry film thickness 80 µm																				
■ Clear coat	RRS W CLEARCOAT HG Dry film thickness 30 µm																				
Mechanical Test	<table border="1"> <tr> <td>■ Cross-cut-test DIN EN ISO 2409</td> <td>Gt 0</td> </tr> </table>	■ Cross-cut-test DIN EN ISO 2409	Gt 0																		
■ Cross-cut-test DIN EN ISO 2409	Gt 0																				

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



Hydro-Clearcoat

WO1868GR999A / RRS W CLEARCOAT HG

	<ul style="list-style-type: none"> Stone chipping test DIN EN ISO 20567-1 	Characteristic value 1
	<ul style="list-style-type: none"> Salt spray test (CASS) DIN EN ISO 9227 	240 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8
Processing and application	<ul style="list-style-type: none"> Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water. 	
	<ul style="list-style-type: none"> Object temperature 	40-60 °C
	<ul style="list-style-type: none"> Processing conditions 	Room temperature 15-25 °C Relative humidity 50-70 %
	<ul style="list-style-type: none"> High pressure spraying 	as delivered viscosity Nozzle: 1,3 mm Spray pressure 3 bar
	<ul style="list-style-type: none"> Electrostatic 	possible, system-specific
	<ul style="list-style-type: none"> ESTA high rotation 	as delivered viscosity
	<ul style="list-style-type: none"> Cleaning of equipment 	Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-onequipment with org.solvents, e.g. RRS SOLV 4320
	<ul style="list-style-type: none"> Health & Safety at Work guidelines The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health & Safety at Work and environmental protection can be found in the corresponding safety data sheet. 	
Curing	<ul style="list-style-type: none"> Oven drying 	15 min./ 160 °C
	<ul style="list-style-type: none"> Object temperature Baking window on request 	
Resistance to storage	<ul style="list-style-type: none"> Approx. 9 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time. 	
		The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.
Specific comments	<ul style="list-style-type: none"> Test conditions All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information. 	
		The information provided here contains reference values and does not constitute a specification.