


# Hydro-Basecoat

## WO1869A / RRS W02

<b>Characteristics</b>	<ul style="list-style-type: none"> <li>■ Water-thinnable baking coating</li> <li>■ Application, e.g. in the automotive sector</li> <li>■ Good stone chip resistance</li> <li>■ Can be coated over with powder coatings</li> </ul>																						
<b>Technical / Physical Data</b>	<table border="1"> <tr> <td>■ Binder-Base</td> <td>Combination of polyester/amino resin</td> </tr> <tr> <td>■ Colour</td> <td>glazing</td> </tr> <tr> <td>■ Gloss value visual</td> <td>satin glossy</td> </tr> <tr> <td>■ Viscosity DIN 53211 (formerly)</td> <td>Flow time 18-20 seconds 4 mm viscosity cup</td> </tr> <tr> <td>■ Thinner</td> <td>demineralised water</td> </tr> <tr> <td>■ pH-Value</td> <td>8,0-8,4</td> </tr> <tr> <td>■ Density calculated</td> <td>1,00-1,03 g/ml</td> </tr> <tr> <td>■ Solid Mass calculated</td> <td>15-19 %</td> </tr> <tr> <td>■ Solid content in volume calculated</td> <td>130-150 ml/kg</td> </tr> <tr> <td>■ Material usage theoretical, without application loss</td> <td>100-115 g/m<sup>2</sup>, Layer thickness 15 µm</td> </tr> <tr> <td>■ Reference colour of the specified values</td> <td>Colour of WO1869APS20A</td> </tr> </table>	■ Binder-Base	Combination of polyester/amino resin	■ Colour	glazing	■ Gloss value visual	satin glossy	■ Viscosity DIN 53211 (formerly)	Flow time 18-20 seconds 4 mm viscosity cup	■ Thinner	demineralised water	■ pH-Value	8,0-8,4	■ Density calculated	1,00-1,03 g/ml	■ Solid Mass calculated	15-19 %	■ Solid content in volume calculated	130-150 ml/kg	■ Material usage theoretical, without application loss	100-115 g/m <sup>2</sup> , Layer thickness 15 µm	■ Reference colour of the specified values	Colour of WO1869APS20A
■ Binder-Base	Combination of polyester/amino resin																						
■ Colour	glazing																						
■ Gloss value visual	satin glossy																						
■ Viscosity DIN 53211 (formerly)	Flow time 18-20 seconds 4 mm viscosity cup																						
■ Thinner	demineralised water																						
■ pH-Value	8,0-8,4																						
■ Density calculated	1,00-1,03 g/ml																						
■ Solid Mass calculated	15-19 %																						
■ Solid content in volume calculated	130-150 ml/kg																						
■ Material usage theoretical, without application loss	100-115 g/m <sup>2</sup> , Layer thickness 15 µm																						
■ Reference colour of the specified values	Colour of WO1869APS20A																						
<b>Substrate</b>	<ul style="list-style-type: none"> <li>■ Light alloy wheels</li> </ul>																						
<b>Pretreatment</b>	<ul style="list-style-type: none"> <li>■ The substrate must be free of adhesion-impairing substances such as oil, grease, rust, scale, rolling skin, wax and separating agent residue. Preliminary tests are recommended for assuring the suitability of coating qualities on the substrate. Chromating or corresponding chrome-free conversion coatings.</li> </ul>																						
<b>Structure recommendation</b>	<table border="1"> <tr> <td>■ Substrate</td> <td>on light alloy wheels</td> </tr> <tr> <td>■ Primer</td> <td>RRS CLEARCOAT PE/AC Dry film thickness 90 µm</td> </tr> <tr> <td>■ Base coat</td> <td>RRS W02 Dry film thickness 15 µm</td> </tr> <tr> <td>■ Clear coat</td> <td>RRS CLEARCOAT AC Dry film thickness 90 µm</td> </tr> </table>	■ Substrate	on light alloy wheels	■ Primer	RRS CLEARCOAT PE/AC Dry film thickness 90 µm	■ Base coat	RRS W02 Dry film thickness 15 µm	■ Clear coat	RRS CLEARCOAT AC Dry film thickness 90 µm														
■ Substrate	on light alloy wheels																						
■ Primer	RRS CLEARCOAT PE/AC Dry film thickness 90 µm																						
■ Base coat	RRS W02 Dry film thickness 15 µm																						
■ Clear coat	RRS CLEARCOAT AC Dry film thickness 90 µm																						
<b>Mechanical Test</b>	<table border="1"> <tr> <td>■ Cross-cut-test DIN EN ISO 2409</td> <td>Gt 0</td> </tr> <tr> <td>■ Stone chipping test DIN EN ISO 20567-1</td> <td>Characteristic value &lt;2</td> </tr> </table>	■ Cross-cut-test DIN EN ISO 2409	Gt 0	■ Stone chipping test DIN EN ISO 20567-1	Characteristic value <2																		
■ Cross-cut-test DIN EN ISO 2409	Gt 0																						
■ Stone chipping test DIN EN ISO 20567-1	Characteristic value <2																						
<b>Resistance Test</b>	<table border="1"> <tr> <td>■ Condensate constant climate DIN EN ISO 6270-2 (CH)</td> <td>240 hours Degree of blistering 0 (S 0) DIN EN ISO 4628-2</td> </tr> </table>	■ Condensate constant climate DIN EN ISO 6270-2 (CH)	240 hours Degree of blistering 0 (S 0) DIN EN ISO 4628-2																				
■ Condensate constant climate DIN EN ISO 6270-2 (CH)	240 hours Degree of blistering 0 (S 0) DIN EN ISO 4628-2																						

Our technical data sheets are to provide you with advice based on our latest state of knowledge. This guidance does not release you from your own obligation to test our products for their suitability for your intended purposes and applications. The sale of our products is in accordance with our terms of business and delivery.



# Hydro-Basecoat

## WO1869A / RRS W02

	<ul style="list-style-type: none"> <li>■ Salt spray test (CASS) DIN EN ISO 9227</li> </ul>	240 hours Water ingress Wb < 1 mm DIN EN ISO 4628-8
<b>Processing and application</b>	<ul style="list-style-type: none"> <li>■ Prior to use, stir well or mix components homogeneously (e.g. with fast mixer). To prevent skin formation, over-coat with water.</li> </ul>	
	<ul style="list-style-type: none"> <li>■ Object temperature</li> </ul>	50 °C
	<ul style="list-style-type: none"> <li>■ Processing conditions</li> </ul>	Room temperature 15-25 °C Relative humidity 50-70 %
	<ul style="list-style-type: none"> <li>■ Electrostatic</li> </ul>	possible, system-specific
	<ul style="list-style-type: none"> <li>■ ESTA high rotation</li> </ul>	as delivered viscosity
	<ul style="list-style-type: none"> <li>■ Cleaning of equipment</li> </ul>	Immediately with water - possibly with addition of 5-10 % by weight EFD cleaning agent 400916. Dried-onequipmentwith org.solvents, e.g. thinner RRS SOLV 4320
	<ul style="list-style-type: none"> <li>■ <b>Health &amp; Safety at Work guidelines</b> The standard personal safety precautions must be observed when handling painting materials. Detailed information about dangerous substances, safety data and recommendations concerning Health &amp; Safety at Work and environmental protection can be found in the corresponding safety data sheet.</li> </ul>	
<b>Curing</b>	<ul style="list-style-type: none"> <li>■ Intermediate drying</li> </ul>	10 min./ 120 °C
	<ul style="list-style-type: none"> <li>■ Oven drying</li> </ul>	10 min./ 180 °C - 20 min./ 170 °C
	<ul style="list-style-type: none"> <li>■ <b>Object temperature</b> Baking window on request</li> </ul>	
<b>Resistance to storage</b>	<ul style="list-style-type: none"> <li>■ Approx. 9 month in original packagings at an ambient temperature of 5 to 25 °C. Protect from frost. Open packages are to be used within a short time.</li> </ul>	
		The minimum storage stability of each batch is stated on the product label. The material does not necessarily become unusable if stored for longer than this period. However, for quality assurance purposes, an inspection of these materials is essential to ensure that they are still suitable for the intended application.
<b>Specific comments</b>	<ul style="list-style-type: none"> <li>■ <b>Test conditions</b> All information is based on a standard climate 23/50 DIN EN 23270. All information is based on our product knowledge and experience. We have no direct influence on the application itself. Please do not hesitate to contact us for further information.</li> </ul>	
		The information provided here contains reference values and does not constitute a specification.